



Product Specifications





IMPACT SERIES PRO

- Ultra Gloss Enhancing
- Self-Healing W/Heat
- Non-Yellowing
- Mid-initial Tack
- Max Stretchability




Warranty Coverage	Yellowing, Staining, Cracking, Blistering, Delaminating	
Thickness	8 mil / 200 UM	
Self-Healing Thickness	15 UM	
Base Film Thickness	150um±8	
Adhesive Thickness	25 UM	
Gloss	97	
Tensile Strength	33.9Mpa	
Tear Strength	65.1 KN/m	
Elongation at Break	≥430%	
100% Modulus	6.9Mpa	
Anti-yellowing	ΔΕ<1	
Hydrophobic Property	>RIO	
Peeling Force of	20min	24h
Acrylic Adhesive layer	937 gf/inch	1498 gf/inch
Durability	Zone 1	Zone 2
	Lifetime	Lifetime



PRO WIDE

- Ultra Gloss Enhancing
- Self-Healing W/Heat
- Non-Yellowing
- Mid-initial Tack
- Max Stretchability




Warranty Coverage	Yellowing, Staining, Cracking, Blistering, Delaminating	
Thickness	8 mil / 200 UM	
Self-Healing Thickness	15 UM	
Base Film Thickness	15Oum±8	
Adhesive Thickness	25 UM	
Gloss	97	
Tensile Strength	33.9Mpa	
Tear Strength	65.1 KN/m	
Elongation at Break	≥430%	
100% Modulus	6.9Mpa	
Anti-yellowing	ΔΕ<1	
Hydrophobic Property	>RIO	
Peeling Force of	20min	24h
Acrylic Adhesive layer	937 gf/inch	1498 gf/inch
Durability	Zone 1	Zone 2
	Lifetime	Lifetime



IMPACT SERIES FORCE

- Self-Healing W/Heat
- Non-Yellowing
- Low-initial Tack
- Good Stretchability




Warranty Coverage	Yellowing, Staining, Cracking, Blistering, Delaminating	
Thickness	7.5 mil / 190 UM	
Self-Healing Thickness	15 UM	
Base Film Thickness	15Oum±8	
Adhesive Thickness	25 UM	
Gloss	94.6	
Tensile Strength	23.66Mpa	
Tear Strength	86.1 KN/m	
Elongation at Break	≥325%	
100% Modulus	9.14Mpa	
Anti-yellowing	ΔE< 1.2	
Hydrophobic Property	>RIO	
Peeling Force of	20min	24h
Acrylic Adhesive layer	1272 gf/inch	2525 gf/inch
Durability	Zone 1	Zone 2
	5 Years	3 Years



IMPACT SERIES OFF-ROAD¹²

- Ultra Gloss Enhancing
- Self-Healing W/Heat
- Non-Yellowing
- Mid-initial Tack




600	blisterii ig, Delai i ili la	11119
Thickness	12 mil / 300 UN	И
Self-Healing Thickness	15 UM	
Base Film Thickness	27Oum±8	
Adhesive Thickness	25 UM	
Gloss	95.3	
Tensile Strength	21.7Mpa	
Tear Strength	72.3 KN/m	
Elongation at Break	≥400%	
100% Modulus	9.14Mpa	
Anti-yellowing	ΔE< 1.2	
Hydrophobic Property	R9-R1O	
Peeling Force of	20min	24h
Acrylic Adhesive layer	1783 gf/inch	2325 gf/inch
	Zone 1	Zone 2
Durability	10 Years	7 Years



IMPACT SERIES SATIN

- Self-Healing W/Heat
- Non-Yellowing
- Mid-initial Tack
- Excellent Stretchability




Warranty Coverage	Blistering, Delaminating	
Thickness	7.5 mil / 190 UM	1
Self-Healing Thickness	15 UM	
Base Film Thickness	150um±8	
Adhesive Thickness	25 UM	
Gloss	18.7	
Tensile Strength	23.66Mpa	
Tear Strength	60.3 KN/m	
Elongation at Break	≥375%	
100% Modulus	23.7Mpa	
Anti-yellowing	ΔE< 1.5	
Hydrophobic Property	R9-R1O	
Peeling Force of	20min	24h
Acrylic Adhesive layer	2144 gf/inch	2378 gf/inch
	Zone 1	Zone 2
Durability	10 Years	7 Years



HEAD/TAIL LIGHT

30% 50% **70**% Simple to install Headlight and Taillight Film



Warranty Coverage	Yellowing, Staining, Blistering, Delamina	
Thickness	8 mil / 200 UM	
Self-Healing Thickness	15 UM	
Base Film Thickness	150um±8	
Adhesive Thickness	25 UM	
Gloss	92.8	
Tensile Strength	24.1 Mpa	
Tear Strength	58.4 KN/m	
Elongation at Break	≥350%	
100% Modulus	6.7 Mpa	
Anti-yellowing	ΔΕ< 1.5	
Hydrophobic Property	R9-RIO	
Peeling Force of	20min	24h
Acrylic Adhesive layer	1152 gf/inch	1848 gf/inch
Durability	Zone 1	Zone 2
	10 years	7 years



Shades







Specialty Iridescent











Classics































