

THERMOREFLEX™ EXTRA

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	140- 150 microns	non adhesive polyester	REACH n° 1907/2006/EU EN 20471 OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 19.HIT.86736 HOHENSTEIN HTTI

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
nylon, polyester, treated fabrics, leather	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	70-100gf with new blade, 130gf with a used blade	20 cm/sec	5+10 seconds	160°C (320°F)	Medium (2,5/3,5 bar)	warm

- Remove the protective film
- Mirror cut the material
- Peel off excess material
- Place the decoration on the fabric
- Transfer for 5" under the suggested conditions
- Remove the carrier in warm conditions
- Cover with baking paper
- Press another 10" for final fixing

PRODUCT HIGHLIGHTS

- Applicable on difficult fabrics (nylon, treated fabrics)

NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID: 9105027958

